


Identity file :



Colour : **beige, with +/- apparent veins**
 Quality grain : **medium grain**
 Basin : **Nivernais**
 Extraction site : **DONZY (58)**
 Possible finishes : **Antique brushing, Antique rolling, Bush hammered, Chiselled, ground, Honed, Polished, Rough, Spalled**
 Possibility of large volumes : **no**
 Possibility of formats >2m : **no**
 Floor heating : **yes**

Possible uses :

	INTERIOR	EXTERIOR
Tiling, paving		
Floor tiling	X	X
Heavy public traffic		
Moderate public traffic	X	X
Private traffic	X	X
Cladding		
Band	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Wall coping	X	X
Wall covering		
Window support	X	X
Stone wall		
Band	X	X
Buttress	X	X
Cornice	X	X
Crown	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Solid stone elements		
	X	

References :

Baths of Vichy. Towns of Cosne sur Loire and Sancerre

Identification file :

	Unit of measure	maxi	mini	average	norm
Open porosity	%	-	-	-	-
Density/Apparent volumetry mass	kg/M ³	-	-	-	-
Capillarity coefficient C¹	g.m ⁻² -1/2	-	-	-	-
Capillarity coefficient C²	g.m ⁻² -1/2	8.3	5.4	6.8	NFEN 772-11
Wear on disk	mm	23.4	18.6	21.5	EN 14157
Bending strength	M Pa	9.9	5.3	8.4 N/mm ²	NFB 10510
Fastener strength (type i)	N	-	-	-	-
Fastener strength (type IIa)	N	-	-	-	-
Fastener strength (type IIb)	N	-	-	-	-
Compression strength	M Pa	95.1	61.9	81	NFEN 1926
Compression strength 2		-	-	-	-
Frost resistance	Nb. de cycle	-	-	144	EN 12371
Slipperiness – dry environment		-	-	-	-
Slipperiness – wet environment		69	60	63	NFEN 1341 FINITION: brut de sciage