

POUILLENAY GRIS BEIGE ROSE

Identity file :



Colour : **pink, beige, grey beige**
Quality grain : **large grain, gritty aspect**
Basin : **Mâconnais**
Extraction site : -
Possible finishes : **Bossed, Bush hammered, Chiselled, Flamed, Honed, Polished, Rough, Spalled, Toothed**
Possibility of large volumes : **yes**
Possibility of formats >2m : **yes**
Floor heating : **yes**

Possible uses :

	INTERIOR	EXTERIOR
Tiling, paving		
Floor tiling	X	X
Heavy public traffic		
Moderate public traffic	X	X
Private traffic	X	X
Cladding		
Band	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Wall coping	X	X
Wall covering		
Window support	X	X
Stone wall		
Band	X	X
Buttress	X	X
Cornice	X	X
Crown	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Solid stone elements		
	X	X

References :

Chrystal Park - Neuilly. Office buildings - bd Saint Germain and rue de l'Université - Paris. National Gallery - Playfair - Edimbourg.

Identification file :

	Unit of measure	maxi	mini	average	norm
Open porosity	%	8	4	6	NFEN 1936
Density/Apparent volumetry mass	kg/M ³	2600	2500	2600	NFEN 1936
Capillarity coefficient C ¹	g.m ⁻² -1/2	60	30	45	NFEN 1925
Capillarity coefficient C ²	g.m ⁻² -1/2	60	30	45	NFEN 1925
Wear on disk	mm	32	28	30	NFEN 1341
Bending strength	M Pa	-	-	-	-
Fastener strength (type i)	N	180	150	180	NFEN 13364
Fastener strength (type IIa)	N	-	-	-	-
Fastener strength (type IIb)	N	-	-	-	-
Compression strength	M Pa	80	40	60	NFEN 1926
Compression strength 2		-	-	-	-
Frost resistance	Nb. de cycle	-	-	-	-
Slipperiness – dry environment		-	-	-	-
Slipperiness – wet environment		-	-	-	-