

Identity file :



Colour : **golden/yellow, beige, grey-beige to pink, ribboned**
 Quality grain : **fine grain, ribboned**
 Basin : **La Côte**
 Extraction site : **VILLIERS LA FAYE (21)**
 Possible finishes : **Antique brushing, Antique rolling, Bossed, Bush hammered, Chiselled, Flamed, ground, Honed, Polished, Rough, Spalled**
 Possibility of large volumes : **yes**
 Possibility of formats >2m : **yes**
 Floor heating : **yes**

Possible uses :

	INTERIOR	EXTERIOR
Tiling, paving		
Floor tiling	X	X
Heavy public traffic	X	X
Moderate public traffic	X	X
Private traffic	X	X
Cladding		
Band	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Wall coping	X	X
Wall covering		
Window support	X	X
Stone wall		
Band	X	X
Buttress	X	X
Cornice	X	X
Crown	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Solid stone elements		
	X	X

References :

CPAM - Ancey. Expo Park - Epernay. Mall - Lille, Nomura Bank House - London. SG Samsung - South Korea

Identification file :

	Unit of measure	maxi	mini	average	norm
Open porosity	%	2	1	2	NFEN 1936
Density/Apparent volumetry mass	kg/M ³	2700	2600	2700	NFEN 1936
Capillarity coefficient C¹	g.m ⁻² -1/2	-	-	-	-
Capillarity coefficient C²	g.m ⁻² -1/2	-	-	-	-
Wear on disk	mm	24	20	22	NFEN 1341
Bending strength	M Pa	16	11	14	NFEN 12372
Fastener strength (type i)	N	220	180	200	NFEN 13364
Fastener strength (type IIa)	N	-	-	-	-
Fastener strength (type IIb)	N	-	-	-	-
Compression strength	M Pa	130	100	115	NFEN 1926
Compression strength 2		-	-	-	-
Frost resistance	Nb. de cycle	-	-	-	-
Slipperiness – dry environment		-	-	-	-
Slipperiness – wet environment		-	-	-	-