

**Identity file :**



Colour : **golden/yellow, beige, grey-beige to pink, ribboned**  
 Quality grain : **fine grain, ribboned**  
 Basin : **La Côte**  
 Extraction site : **VILLIERS LA FAYE (21)**  
 Possible finishes : **Antique brushing, Antique rolling, Bossed, Bush hammered, Chiselled, Flamed, ground, Honed, Polished, Rough, Spalled**  
 Possibility of large volumes : **yes**  
 Possibility of formats >2m : **yes**  
 Floor heating : **yes**

**Possible uses :**

	INTERIOR	EXTERIOR
<b>Tiling, paving</b>		
Floor tiling	X	X
Heavy public traffic	X	X
Moderate public traffic	X	X
Private traffic	X	X
<b>Cladding</b>		
Band	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
Wall coping	X	X
Wall covering		
Window support	X	X
<b>Stone wall</b>		
Band	X	X
Buttress	X	X
Cornice	X	X
Crown	X	X
Elevation	X	X
Foundation	X	X
Projections	X	X
<b>Solid stone elements</b>		
	X	X

**References :**

CPAM - Ancey. Expo Park - Epernay. Mall - Lille, Nomura Bank House - London. SG Samsung - South Korea

**Identification file :**

	Unit of measure	maxi	mini	average	norm
<b>Open porosity</b>	%	2	1	2	NFEN 1936
<b>Density/Apparent volumetry mass</b>	kg/M <sup>3</sup>	2700	2600	2700	NFEN 1936
<b>Capillarity coefficient C<sup>1</sup></b>	g.m <sup>-2</sup> -1/2	-	-	-	-
<b>Capillarity coefficient C<sup>2</sup></b>	g.m <sup>-2</sup> -1/2	-	-	-	-
<b>Wear on disk</b>	mm	24	20	22	NFEN 1341
<b>Bending strength</b>	M Pa	16	11	14	NFEN 12372
<b>Fastener strength (type i)</b>	N	220	180	200	NFEN 13364
<b>Fastener strength (type IIa)</b>	N	-	-	-	-
<b>Fastener strength (type IIb)</b>	N	-	-	-	-
<b>Compression strength</b>	M Pa	130	100	115	NFEN 1926
<b>Compression strength 2</b>		-	-	-	-
<b>Frost resistance</b>	Nb. de cycle	-	-	-	-
<b>Slipperiness – dry environment</b>		-	-	-	-
<b>Slipperiness – wet environment</b>		-	-	-	-