

## SAINT MARTIN BELLE ROCHE

### Identity file :



Colour : **beige**  
Quality grain : **fine to medium grain**  
Basin : **Mâconnais**  
Extraction site : -  
Possible finishes : **Flamed, Honed, Polished**  
Possibility of large volumes : **yes**  
Possibility of formats >2m : **yes**  
Floor heating : **yes**

### Possible uses :

INTERIOR EXTERIOR

#### Tiling, paving

Floor tiling  
Heavy public traffic  
Moderate public traffic  
Private traffic

#### Cladding

Band  
Elevation  
Foundation  
Projections  
Wall coping  
Wall covering  
Window support

#### Stone wall

Band  
Buttress  
Cornice  
Crown  
Elevation  
Foundation  
Projections

#### Solid stone elements

### References :

Façade of Coca Cola building Issy les Moulineaux (92), Austerlitz Train Station, Place Valhubert Paris, Grimaldi Forum - Monaco, Place Voltaire - Ivry sur Seine

### Identification file :

	Unit of measure	maxi	mini	average	norm
Open porosity	%	-	-	0.56	-
Density/Apparent volumetry mass	kg/M <sup>3</sup>	-	-	2.66	-
Capillarity coefficient C <sup>1</sup>	g.m <sup>-2</sup> -1/2	-	-	-	-
Capillarity coefficient C <sup>2</sup>	g.m <sup>-2</sup> -1/2	-	-	-	-
Wear on disk	mm	-	-	29.1	-
Bending strength	M Pa	-	-	-	-
Fastener strength (type i)	N	-	-	231	-
Fastener strength (type IIa)	N	-	-	-	-
Fastener strength (type IIb)	N	-	-	-	-
Compression strength	M Pa	-	-	-	-
Compression strength 2	N/mm <sup>2</sup>	-	-	116	-
Frost resistance	Nb. de cycle	240	-	240	-
Slipperiness – dry environment		-	-	-	-
Slipperiness – wet environment		-	-	-	-