

SAINT MARTIN BELLE ROCHE

Identity file :



Colour : **beige**
Quality grain : **fine to medium grain**
Basin : **Mâconnais**
Extraction site : -
Possible finishes : **Flamed, Honed, Polished**
Possibility of large volumes : **yes**
Possibility of formats >2m : **yes**
Floor heating : **yes**

Possible uses :

INTERIOR EXTERIOR

Tiling, paving

Floor tiling
Heavy public traffic
Moderate public traffic
Private traffic

Cladding

Band
Elevation
Foundation
Projections
Wall coping
Wall covering
Window support

Stone wall

Band
Buttress
Cornice
Crown
Elevation
Foundation
Projections

Solid stone elements

References :

Façade of Coca Cola building Issy les Moulineaux (92), Austerlitz Train Station, Place Valhubert Paris, Grimaldi Forum - Monaco, Place Voltaire - Ivry sur Seine

Identification file :

| | Unit of measure | maxi | mini | average | norm |
|--|------------------------|------|------|---------|------|
| Open porosity | % | - | - | 0.56 | - |
| Density/Apparent volumetry mass | kg/M ³ | - | - | 2.66 | - |
| Capillarity coefficient C ¹ | g.m ⁻² -1/2 | - | - | - | - |
| Capillarity coefficient C ² | g.m ⁻² -1/2 | - | - | - | - |
| Wear on disk | mm | - | - | 29.1 | - |
| Bending strength | M Pa | - | - | - | - |
| Fastener strength (type i) | N | - | - | 231 | - |
| Fastener strength (type IIa) | N | - | - | - | - |
| Fastener strength (type IIb) | N | - | - | - | - |
| Compression strength | M Pa | - | - | - | - |
| Compression strength 2 | N/mm ² | - | - | 116 | - |
| Frost resistance | Nb. de cycle | 240 | - | 240 | - |
| Slipperiness – dry environment | | - | - | - | - |
| Slipperiness – wet environment | | - | - | - | - |