

SAINT REMY CLAIR

Identity file :



Colour : **beige, pinkish veins, beige to light yellow, more or less leafy patterns**
 Quality grain : **Fine grain**
 Basin : **Châtillonnais**
 Extraction site : **NOD SUR SEINE (21)**
 Possible finishes : **Antique brushing, Antique rolling, Bossed, Bush hammered, Chiselled, ground, Honed, Rough, Spalled**
 Possibility of large volumes : **no**
 Possibility of formats >2m : **no**
 Floor heating : **yes**

Possible uses :

	INTERIOR	EXTERIOR
Tiling, paving		
Floor tiling	X	X
Heavy public traffic		
Moderate public traffic	X	X
Private traffic	X	X
Cladding		
Band	X	X
Elevation	X	X
Foundation	X	
Projections	X	X
Wall coping	X	
Wall covering		
Window support	X	X
Stone wall		
Band	X	X
Buttress	X	X
Cornice	X	
Crown	X	
Elevation	X	X
Foundation	X	
Projections	X	X
Solid stone elements		
	X	X

References :

Collège Jean Mermoz - Angers. Lycée Charles de Gaulle - Dijon. 50 Tritton Square - London.

Identification file :

	Unit of measure	maxi	mini	average	norm
Open porosity	%	25	20	23	NFEN 1936
Density/Apparent volumetry mass	kg/M ³	2100	2000	2100	NFEN 1936
Capillarity coefficient C¹	g.m ⁻² -1/2	-	-	-	-
Capillarity coefficient C²	g.m ⁻² -1/2	-	-	-	-
Wear on disk	mm	42	30	36	NFEN 1341
Bending strength	M Pa	7	5	6	NFEN 12372
Fastener strength (type i)	N	-	-	-	-
Fastener strength (type IIa)	N	-	-	-	-
Fastener strength (type IIb)	N	-	-	-	-
Compression strength	M Pa	-	-	-	-
Compression strength 2		-	-	-	-
Frost resistance	Nb. de cycle	-	-	-	-
Slipperiness – dry environment		-	-	-	-
Slipperiness – wet environment		-	-	-	-